

# Aral Antifreeze Silikatfrei

OA Technology



## Description

A nitrite, amine, phosphate and silicate-free coolant containing ethylene glycol. It has been developed to meet the growing demand from manufacturers for a higher performance coolant based on organic acid technology (OAT).

- Aqueous solutions act as both an antifreeze and coolant and impart very good anti-corrosion protection to all metal parts found in the cooling systems especially for latest full aluminum engines

## Application

Recommended mixtures in water are:.

-20°C with 33 Vol% Aral Antifreeze Silikatfrei

-27°C with 40 Vol% Aral Antifreeze Silikatfrei

-40°C with 50 Vol% Aral Antifreeze Silikatfrei

## Typical Characteristics

Name	Method	Units	Aral Antifreeze Silikatfrei
pH, Engine Coolants / Antirusts	ASTM D1287	-	8.5
Foam, break time	ASTM D1881	seconds	1
Appearance	Visual	-	Pink Mobile Liquid - Clear & Bright
Water	ASTM D1123	% wt	2.2
Flash Point, COC	DIN-ISO 2592	°C	-
Foam, Tendency of Engine Coolants	ASTM D1881	ml	35
Reserve Alkalinity	ASTM D1121	ml 0.1N HCl	8.9
Boiling Point of Engine Coolants	ASTM D1120	°C	177

## Product Performance Claims

ASTM D3306 (I)  
ASTM D4985  
BS6580:2010  
JIS K2234  
MAN 324 Typ SNF  
MB-Approval 325.3

## Storage

All packages should be stored under cover. Where outside storage is unavoidable drums should be laid horizontally to avoid the possible ingress of water and damage to drum markings. Products should not be stored above 60°C, exposed to hot sun or freezing conditions.

Aral Antifreeze Silikatfrei  
28 Apr 2016  
Aral, the Aral logo and related marks are trademarks of Aral Aktiengesellschaft, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Aral Aktiengesellschaft, Geschäftsbereich Schmierstoffe, Überseeallee 1, D-20457 Hamburg  
01801-11 55 11  
[www.aral-lubricants.de](http://www.aral-lubricants.de)