Aral Vitam VF 46 Hydraulic oil

Applications:

Aral Vitam VF 46 is a high quality product based on mineral oil, that guarantees a high function and operational safety. The capabilities of this high VI hydraulic oil exceeds the requirements of DIN 51524-3 for HVLP-D oils. The excellent viscosity temperature performance of this oil is its special quality characteristic. With an optimal operational viscosity over a wide temperature range, this hydraulic oil is guaranteed to maintain its high performance even at very low temperatures. The high viscosity index gives Aral Vitam VF 46 multiple characteristics, and makes it possible to cover with quality, several viscosity classes. In addition it has a good corrosion prevention, excellent ageing stability and reaches an outstanding wearing protection with a high measure of efficiency.

Operational area:

The quality Vitam VF 46 is usable for all hydraulic systems that need precise control, in large variations of temperature, as long as no special precision oils are required by the systems manufacturer. This product is recommended for the use on, heavy duty construction equipment, hydraulic systems on utility vehicles, production presses, auxiliary engines, numerically controlled machine tools and conveyors.

Technical Data

| Density at 15 °C | g/ml | DIN 51757 | 0,874 |
|----------------------------|-------------|-----------------|----------|
| Viscosity | | | |
| 0 °C | mm²/s | DIN 51562 | 395 |
| 40 °C | mm²/s | DIN 51562 | 46 |
| 100 °C | mm²/s | DIN 51562 | 8,07 |
| Viscosity Index | | DIN ISO 2909 | 149 |
| Pourpoint | °C | DIN ISO 3016 | -45 |
| Flash point COC | °C | DIN ISO 2592 | 208 |
| Oxide ash | Gew.% | DIN EN ISO 6245 | <0,01 |
| Neutralization number | mg KOH/g | DIN 51558-1 | 0,15 |
| Ageing characteristics | | | |
| Increase n.n. after 1000 h | mgKOH/g | DIN 51587 | <2,0 |
| Air release time at 50 °C | min | DIN 51381 | <=10 |
| Corrosiveness | | | |
| on copper | Korr. Grad. | DIN EN ISO 2160 | 1-100 A3 |
| on steel | Korr. Grad. | DIN ISO 7120 | 0-A |
| Foaming characteristics | | | |
| at 24 °C | ml | ISO 6247 | <150/0 |
| at 95 °C | ml | ISO 6247 | <75/0 |
| at 24 °C after 95 °C | ml | ISO 6247 | <150/0 |
| FZG test A/8,3/90 | SKS | DIN 51354-2 | >=12 |
| | | | |

Remarks:

<hr>>

All data is subject to development for the product and the production process. Version-No.: IS3108050011